

ABS+HS

Technical Data Sheet

Excellent mechanical strength, impact resistance, and heat resistance, capable of maintaining stable performance under higher loads and complex environments, making it an ideal choice for users with higher demands for durability and strength.

Basic Information

Characteristics	<ul style="list-style-type: none"> • Heat resistance ,strong • Low odor, low shrinkage rate • High-speed print
Applications	<ul style="list-style-type: none"> • Industrial parts • Mechanical teaching aids • Multi-piece production
Forming Method	<ul style="list-style-type: none"> • Filament
Processing Method	<ul style="list-style-type: none"> • 3D Printing

Physical Properties

Testing Method

Data

Density	GB/T 1033	1.04 g/cm ³
Melt Flow Index	GB/T 3682	6 (220°C/10kg)

Thermal Properties

Testing Method

Data

Heat Distortion Temperature	GB/T 1634	89 °C (0.45Mpa)
Glass Transition Temperature		N/A
Continuous Service Temperature	IEC 60216	N/A
Maximum (short term) Use Temperature		N/A

Electrical Properties

Testing Method

Data

Insulation Resistance	DIN IEC 60167	N/A
Surface Resistance	DIN IEC 60093	N/A

Mechanical Properties	Testing Method	Data
Tensile Strength (X-Y)	GB/T 1040	41.64 Mpa
Tensile Strength (Z)	GB/T 1040	27.08 MPa
Elongation at Break (X-Y)	GB/T 1040	5.14 %
Elongation at Break (Z)	GB/T 1040	3.4 %
Flexural Strength (X-Y)	GB/T 9341	46 MPa
Flexural Strength (Z)	GB/T 9341	44.5 Mpa
Flexural Modulus (X-Y)	GB/T 9341	2349.32 MPa
Flexural Modulus (Z)	GB/T 9341	1934.88 Mpa
IZOD Impact Strength (X-Y)	GB/T 1843	25.94 KJ/m ²
IZOD Impact Strength (Z)	GB/T 1843	3.14KJ/m ²


Chemical Properties	Data
Acid and Alkali Resistance	N/A
Grease Resistance	N/A
UV Resistance	N/A
Water Repellency	N/A

Recommended Printing Parameters	Data
Drying Preparation	60°C > 8H
Nozzle Size	0.2,0.4,0.6,0.8mm
Nozzle Temperature	230-270°C
Build Platform Type	PEI
Build Platform Temperature	95-110°C
Fan Speed	0%
Printing Speed	< 300mm/s


Printing Tips

When slicing, it is best to turn on the Z seam alignment and starting point alignment functions, turn off the Z-axis lift and exit, avoid passing through the shell when idling, optimize the slicing printing path, and appropriately reduce the printing speed to achieve the best printing effect.


Test Conditions of Mechanical Properties



Tensile testing specimen GB/T 1040



Flexural testing specimen GB/T 9341



Impact testing specimen GB/T 1843

The performance of the filament is evaluated based on standard samples printed by eSUN, while the actual printing performance is influenced by various factors such as printer type, printing parameters, and print environment.

Printing Test Conditions:

Extruder Temperature	260°C
Build Platform Temperature	100°C
Outer Layer Number	2
Top/Bottom Layer Number	3
Infill Density	100%
Fan Speed	0%

*Based on Bambu P1S 0.4 mm nozzle and Orcaslicer 2.1.0 Beta.

Notice

The information provided by or on behalf of eSUN regarding this product, whether in the form of data, recommendations, or otherwise, is supported by thorough research and believed to be reliable in good faith. However, please note that the product is sold "as is". eSUN assumes no liability and does not make any express or implied representations or warranties regarding the merchantability, fitness for a particular purpose, or any other nature of the information or the product it pertains to. This statement does not waive any conditions of sale set forth by the seller.